

Introduction

KC-205 is a Liquid phenolic resole resin.

Application

KC-205 is used in the production of high pressure laminates (HPL).

Typical Properties

Properties	Standard	Value	Unit
Appearance	-	Clear yellow/brown liquid	-
Viscosity	DIN 4 @25°C	14-17	seconds
Free Formaldehyde	ISO 11402	<1.5	%
PH	ISO 8975	8.8-9.3	-
Solid Content	ISO 8618	54-56	%
Specific Gravity	ISO 3675	1.15-1.18	-

Storage

This product is a heat reactive material and should be stored in closed containers at, or below 20°C. Hence should be stored indoors in dry place. Avoid keeping material exposed to sunlight.

Packaging

KC-205 is supplied in 240kg drums.



Shelf Time

2 months after producing