

Introduction

KC-215 is a high molecular weight Liquid phenolic resole resin.

Application

KC-215 is used for Foam production.

Typical Properties

Properties	Standard	Value	Unit
Appearance	-	Clear brown liquid	-
Viscosity	ISO 2555	3500-4500	cp @25°C
Free Formaldehyde	-	-	%
PH	ISO 8975	6-7	-
Solid Content	ISO 8618	78-82	%
Specific Gravity	ISO 3675	1.2±0.05	-

Storage

This product is a heat reactive material and should be stored in closed containers at, or below 20°C. Hence should be stored indoors in dry place. Avoid keeping material exposed to sunlight.

Packaging

KC-215 is supplied in 240kg drums.



Shelf Time

1 month after producing