

Introduction

KC-403 is an Acrylic-Styrene emulsion resin.

Application

KC-403 is designed for outdoor and indoor paints.

Typical Properties

Properties	Standard	Value	Unit
Tg (Theoretical)	-	10-12	°C
Viscosity (rpm: 3 & spindle: 3 at 25 °c)	ISO 2555	25000-40000	mPa.s (cps)
Acid Value	-	-	-
PH	ISO 5848	7 – 8.5	-
Solid Content	ISO 3251	50±1	%

Storage

This product should not be stored at temperature below 5 °C or above 35°C. Avoid exposure to direct sunshine or heating source and prevent freezing.

Packaging

KC-403 is supplied in 200kg drums.



Shelf Time

6 months after producing